



# Yellow Sealer

XP 2641

# Yellow Sealer

XP 2641

## Applications

In today's industry the strong demands of product quality and performance are coupled with the equally strong demand for commercial competitiveness, as a consequence XP2641 was developed. Ideally used as a moisture barrier/dust suppressant sealer, it can be diluted with water at a ratio of 4 parts water : 1 part XP2641 and used as a visible sealer /binder for concrete surfaces or plasterboard. XP2641 is recommended for use in conjunction with Chemique Adhesives & Sealants range of pedestal adhesives for access flooring applications.

## Application Data

Packaging	Available in 5KG and 20Kg
Application Temperature	Between 5°C and 25°C
Storage Temperature	Prevent from freezing
Storage Life	12 Months in unopened containers.

## Coverage

Approximately 8m<sup>2</sup> per litre (undiluted) or 40m<sup>2</sup> per litre (diluted) dependant on the porosity of the surface to be sealed.

## Substrate Penetration

All surfaces should be sound, dry and fully cured. Free from oil, grease and any loose surface materials.

## Application

XP2641 should be applied by brush, roller or spreader evenly over the surface area taking care to avoid 'puddling'. Cleaning of materials should be done immediately following application, with copious amounts of water. When diluted XP2641 has been applied and allowed to dry, a second dilute coat may be applied to increased depth of colour. All areas coated with XP2641 should be allowed to dry out thoroughly for several days before being worked on to ensure all water has been removed from the surface being sealed.

## Bonding Range and Pressure

Not applicable.

## Cleaning Solvent

Water.

## Dilution Solvent

Water when used as a diluted bonding/sealing agent.

For more information get in touch with us at:

Tel: +44 (0)1384 637 777 | Web: [www.isaacgrainger.co.uk](http://www.isaacgrainger.co.uk)

Fax: +44 (0)1384 637 111 | Email: [sales@isaacgrainger.co.uk](mailto:sales@isaacgrainger.co.uk)

XP2641 is highly pigmented water based PVA floor sealer which may be applied by brush, spreader or roller. The XP2641 formulation contains no volatile solvents and also allows users to comply with the most recent environmental legislation.

## Application Data

Chemical Base	Polyvinyl Acetate
Viscosity	3500-4500cP @ 20°C
Specific Gravity	1.15 – 1.25
Solvents	Water
Non-Volatile Content	38 - 42 %
Flammability	Non-Flammable
Service Temperature	-20°C to 70°C
Colour	Yellow
Chemical Resistance	Resistant to dilute acids, alkalis and oils.
pH	7-8

## Health and Safety Information

Please consult the XP 2641 Material Health and Safety Data Sheets for statutory regulation information.

The information presented on this data sheet is not intended as a formal technical specification and should only be taken as a guideline.